

SIGMA VIKOTE 46**(SIGMA TOPACRYL COATING)**

3 pages

September 2005
Revision of January 2003

DESCRIPTION	high build modified acrylic coating
PRINCIPAL CHARACTERISTICS	<ul style="list-style-type: none"> – buildcoat for above water areas – excellent anticorrosive properties – resistant to water and splash of mild chemicals – fast drying – can be applied at low temperatures, down to -10°C
COLOURS AND GLOSS	offwhite, black, grey, green, redbrown - flat
BASIC DATA AT 20°C	(1 g/cm ³ = 8.25 lb/US gal; 1 m ² /l = 40.7 ft ² /US gal)
Mass density	1.3 g/cm ³
Volume solids	44 ±2%, depending on colour
VOC (supplied)	max. 391 g/kg (Directive 1999/13/EC, SED) max. 494 g/l (approx. 4.1 lb/gal)
Recommended dry film thickness	75 - 100 µm depending on system
Theoretical spreading rate	5.9 m ² /l for 75 µm, 4.4 m ² /l for 100 µm
Touch dry after	1 hour at 5 - 10°C, 30 min. at 20°C
Overcoating interval	min. 8 hours at 5 - 10°C, 4 hours at 20°C max. no limitations
Shelf life (cool and dry place)	at least 24 months
Flash point	27°C
RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES	<ul style="list-style-type: none"> – previous coat; chlorinated rubber primer or modified acrylic coating, dry and free from any contamination – substrate temperature should be at least 3°C above dew point
SYSTEM SPECIFICATION	marine system sheets 3102, 3103, 3104
INSTRUCTIONS FOR USE	<ul style="list-style-type: none"> – stir well before use – the temperature of the paint should preferably be above 15°C, otherwise extra thinner may be required to obtain application viscosity – too much solvent results in reduced sag resistance
AIRLESS SPRAY	
Recommended thinner	Sigma thinner 21-06
Volume of thinner	0 - 3%, depending on required thickness and application conditions
Nozzle orifice	approx. 0.48 - 0.58 mm (= 0.019 - 0.023 in)
Nozzle pressure	12 - 15 MPa (= approx. 120 - 150 bar; 1700 - 2130 p.s.i.)

SIGMA VIKOTE 46

(SIGMA TOPACRYL COATING)

September 2005

AIR SPRAY

Recommended thinner Sigma thinner 21-06
Volume of thinner 6 - 10%, depending on required thickness and application conditions
Nozzle orifice 1.8 - 2 mm
Nozzle pressure 0.3 - 0.4 MPa (= approx. 3 - 4 bar, 43 - 57 p.s.i.)

BRUSH/ROLLER

Recommended thinner Sigma thinner 21-06
Volume of thinner 0 - 3%
max. dft per coat approx. 60 µm

CLEANING SOLVENT

Sigma thinner 21-06

SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets

this is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

Explanation to product data sheets see information sheet 1411
Safety indications see information sheet 1430
Safety in confined spaces and health safety
Explosion hazard - toxic hazard see information sheet 1431

SIGMA VIKOTE 46

(SIGMA TOPACRYL COATING)

September 2005

LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Sigma Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

Sigma Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Sigma Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

The English text of this document shall prevail over any translation thereof.

DS	7350
165243 green	4199052200
165241 redbrown	2008002200
165242 grey	5177052200
154043 offwhite	7001002200
154044 black	8000002200