

Two sheet issue

June 2008

DESCRIPTION

general purpose two component high build polyamide cured coal tar epoxy coating

PRINCIPAL CHARACTERISTICS

- tar epoxy coating for steel and concrete structures
- easy to apply
- relatively long pot life at elevated temperatures
- very good corrosion resistance
- resistant to chemically polluted water
- good abrasion resistance

COLOUR AND GLOSS

brown or black - semi gloss

BASIC DATA AT 20 °C

(for mixed product)

Mass density

approx. 1.4g/cm³

Solids content

approx. 82% by volume

VOC (supplied)

max. 171 g/l

Recommended dry film thickness

75 - 300 µm*

Theoretical spreading rate

10.9 m²/ltr for 75 µm*

Touch dry after

approx. 6 hours

Overcoating interval

min. 6 hours*
max. 20 days*

Full cure after

10 days

Shelf life (cool, dry place)

at least 12 months

Flashpoint

base 27 °C - hardener 28 °C

* see additional data

RECOMMENDED SUBSTRATE CONDITIONS

- concrete; dry and free from any contamination
- steel; immersed conditions; blast cleaned to ISO-Sa2½ atmospheric conditions; power tool cleaned to SPSS-Pt2
- pervious coat of epoxy primer; within overcoating interval and free from any contamination
- substrate temperature must be above 5 °C and at least 3 °C above the dew point

June 2008

INSTRUCTIONS FOR USE

- mixing ratio: by volume; base to hardener 89 : 11
- the temperature of the mixed base and hardener should be above 15 °C, otherwise extra solvent may be required to obtain the correct application viscosity
- too much solvent will result in lower sag resistance and slower cure
- thinner should only be added after proper mixing of the base and hardener

Induction time at 20 °C none

Pot life at 20 °C 6 hours*

AIRLESS SPRAY

Recommended thinner Sigma thinner 91-92 (flashpoint 20 °C)

Volume of thinner 0 - 5%

Nozzle orifice approx. 0.48 mm (0.019 inch)

Nozzle pressure 150 bar (approx. 2100 p.s.i.)

AIR SPRAY

Recommended thinner Sigma thinner 91-92 (flashpoint 20 °C)

Volume of thinner 5 - 10%

Nozzle orifice 1.5 - 3.0 mm

Nozzle pressure 3 - 4 bar (approx. 43 - 57 p.s.i.)

BRUSH AND ROLLER

Recommended thinner Sigma thinner 91-92 (flashpoint 20 °C)

Volume of thinner 0 - 5%

CLEANING SOLVENT

Sigma thinner 90-53 (flashpoint 30 °C)

SAFETY PRECAUTIONS



see safety sheets 1430, 1431 and MSDS 7686 for information on LEL and TLV values

this is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

ADDITIONAL DATA

Film thickness and spreading rate

Dry film thickness in microns (µm)	75	125	200	300
Theoretical spreading rate (m ² /l)	10.9	6.9	4.1	2.7

Minimum dft for closed film with airless spray: 75 µm

Maximum dft for brush application: 75 µm

see sheet two

Sheet two

June 2008

Overcoating table for a dft of 125 - 250 microns

substrate temperature	20 °C	30 °C	40 °C
minimum interval	8 hours	6 hours	5 hours
maximum interval	20 days	18 days	14 days

Curing table

Substrate temperature	Dry to handle	Full cure
20 °C	30 hours	10 days
30 °C	20 hours	5 days
40 °C	12 hours	3 days

adequate ventilation must be maintained during application and curing (refer sheets 1433 and 1434)

Pot life (at application viscosity)

Paint temperature	Pot life
20 °C	6 hours
30 °C	4 hours
40 °C	3 hours

REFERENCES

explanation to product data sheets on information sheet 1411

Limitation of Liability - The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Sigma Paints, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end users responsibility to determine the suitability of the product for its intended use.

Sigma Paints has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Sigma Paints does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development.

This data sheet replaces and annuls all previous issues and it is therefore the users responsibility to ensure that this sheet is current prior to using the product.